

Maqua® Pad MAP



Water-based pad printing ink for coated/uncoated wood, ABS, PVC, PC, pretreated PP, and coated substrates

Satin gloss, high opacity, medium-fast drying speed, for sensitive applications

Vers. 2
2020
19. Oct

Field of Application

Substrates

Maqua® Pad MAP is suited for applications on:

- Wood, coated or uncoated
- ABS
- PVC
- PC

After pre-treatment / cleaning, Maqua® Pad MAP also adheres well to:

- pretreated PP
- coated substrates

When printing on polypropylene, please note that the surface of the substrate must be pre-treated by flaming or corona discharge. Experience has shown that good adhesion can be achieved with a surface tension of at least 48 mN/m.

Since all the print substrates mentioned may be different in printability even within an individual type, preliminary trials are essential to determine the suitability for the intended use.

Field of use

Maqua® Pad MAP is suited for single and multi-color printing, particularly on toys made of absorbent materials. Especially for multicolour printing, adequate air drying is necessary to print multiple ink layers.

Characteristics

Maqua® Pad MAP is suited for applications compliant with the directive 2009/48/EG ("toys directive DIN EN 71/3"). It is made without the use of BPA/BPS, and feature lowest PAH and VOC values.

Ink Adjustment

The ink must be stirred homogeneously before use. The viscosity must be kept on a steady level during production.

Maqua® Pad MAP is press-ready and can be adjusted with Retarder WV 1, if required.

Drying

Maqua® Pad MAP is a medium-fast drying, water-based ink system.

Drying properties **cannot** be compared with that of solvent-based ink systems! During machine stops, the etching of the cliché must always be covered with ink in order to prevent the ink from drying up in the etching. Generally, the drying must always be checked before further processing in order to see if the implementation of an intermediate or final drying process may be necessary.

Maximum printing speed 1200 parts/hour.

Fade resistance

Pigments of medium to high fade resistance are used for the Maqua® Pad MAP range (blue wool scale > 6).

Stress resistance

After proper and thorough drying, the ink film exhibits outstanding adhesion as well as rub, scratch, and block resistance. It is characteristic for water-based ink systems that the chemical and mechanical resistance of the ink film will rise significantly with time. Resistance tests should be carried out at the earliest 7 days after application.

Range

Basic Shades

920	Lemon
922	Light Yellow

Maqua® Pad MAP



924	Medium Yellow
926	Orange
930	Vermilion
932	Scarlet Red
934	Carmine Red
936	Magenta
940	Brown
950	Violet
952	Ultramarine Blue
954	Medium Blue
956	Brilliant Blue
960	Blue Green
962	Grass Green
970	White
980	Black

High Opaque Shades

170	Opaque White
180	Opaque Black

Further Products

910	Overprint Varnish
-----	-------------------

All color shades are intermixable. Mixing with other ink types or auxiliaries must be avoided in order to maintain the special characteristics of this ink.

Auxiliaries

AR	Anti-Rust Additive	5-10%
WV 1	Retarder	3-5%
TPV 2	Thinner, to be used only as cleaner	
UR 3	Cleaner (flp. 42°C)	
PLR	Cleaner	

To adjust the ink, Retarder WV 1 (max. addition 3-5 %) may be added. If needed, viscosity can be regulated with distilled water (max. 2-3 %).

Rusting of low-quality steel clichés can be prevented by adding a maximum of 5-10 % Anti-Rust Additive AR.

It is recommended to use Thinner TPV 2 for cleaning the working equipment, or alternatively Cleaner PLR.

Printing Parameters

Clichés

All commercially available clichés made of ceramic, photopolymer, thin steel (springsteel quality), and chemically hardened steel (10 mm) can be used. The recommended cliché depth is 20-35 µm. A fundamental requirement is the absolute flatness of the base plate when using photopolymer or thin steel clichés. In general, all cliché types must be screened. Photopolymer clichés should be re-exposed with a 120 l/cm halftone with a density of approx. 85 %. For thin steel or steel clichés, an 80 l/cm halftone should be chosen if technically possible.

Printing pads

Experience has shown that best results are achieved with dry or super dry printing pads with a minimum of 8 shore. The pads should be made of materials cross-linked by condensation or addition. The steeper the form of the tampon, the better the printing result.

Printing machines

Maqua® Pad MAP is suited for closed ink cup systems. As for solvent-based ink types, auxiliaries can be added during longer print runs in order to control the ink's viscosity.

Printing conditions

Air humidity must not be lower than 40 % r. F. and should be regulated with an air humidifying system. For best results, the room temperature must be maintained at 20-25°C.

Shelf Life

Maqua® Pad MAP is a water-based ink system and in order to avoid frost damages, it should under no circumstances (not even shortly) be exposed to temperatures lower than 5°C during transport and storage.

If permanently stored at a temperature range of 15-25°C, the shelf life of the unopened ink container is 1 year. Under different conditions, particularly differing storage temperatures, the shelf life is reduced. In such cases, the warranty given by Marabu expires.

Vers. 2
2020
19. Oct

Maqua® Pad MAP



Vers. 2
2020
19. Oct

Note

Our technical advice whether spoken, written, or through test trials corresponds to our current knowledge to inform about our products and their use. This is not meant as an assurance for certain properties of the products nor their suitability for each application.

You are, therefore, obliged to conduct your own tests with our supplied products to confirm their suitability for the desired process or purpose. The foregoing information is based on our experience and should not be used for specification purposes. All characteristics described in this Technical Data Sheet refer exclusively to the standard products listed under "Range", provided that they are processed in accordance with their intended use and only when used with the recommended auxiliaries. The selection and testing of the ink for specific applications is exclusively your responsibility. Should, however, any liability claims arise, they shall be limited to the value of the goods delivered by us and utilised by you with respect to any and all damages not caused intentionally or by gross negligence.

Labelling

For Maqua® Pad MAP and its auxiliaries, there are current Material Safety Data Sheets available according to EC regulation 1907/2006, informing in detail about all relevant safety data including labelling according to EC regulation 1272/2008 (CLP regulation). Such health and safety data may also be derived from the respective label.

Water-based products typically contain isothiazolinone biocides, including methyl isothiazolinone, as in-can preservatives. Such biocides may cause allergic skin reactions in already sensitised individuals.